

# SUPER PLASTICIZER HIGH-RANGE WATER REDUCER FOR CONCRETE

## ASTM C-494 TYPE A & F; AASHTO M-194 TYPE A & F; CRD C-87 TYPE A & F

POLYSTRONG

**DESCRIPTION** PolyStrong is a polycarboxylate-based full range water reducing admixture designed to provide optimum results at all levels of dosage rates. It will meet and exceed the requirements of both Type A (water reducing) and Type F (high-range water reducing) admixtures. The linear dosage characteristics of PolyStrong will improve the properties of concrete in all stages.

**ADVANTAGES** PolyStrong provides the following:

- > Full range of water reduction can be achieved with one product
- > Increases compressive strength and flexural strength performance at all ages
- > Improves the setting times and strength development of concrete in all stages
- > Enhances the pumpability, placement and finishability of all concrete
- > Develops a superior finish on all formed surface
- > Enhances compaction, with minimal vibration
- > Greatly improves all concrete containing Pozzolanic materials

**PERFORMANCE** PolyStrong optimizes the performance of concrete under the most demanding conditions, as shown in the following table:

CONCRETE*	Setting Time		Slump Retention			Compressive Strength					
	Initial Set (h:min)	Difference (h:min)	15 Min.	30 Min.	60 Min.	1 Day		7 Days		28 Days	
						PSI	MPa	PSI	MPa	PSI	MPa
NO ADMIXTURE	4:30	0	8	8	7	2530	17.4	4290	29.6	5960	41.1
CONVENTIONAL HRWR	5:45	+1.15	8.25	5	3.5	3050	21.0	5200	35.9	6800	46.9
<b>POLYSTRONG</b>	4:47	+1.17	9.0	8.75	7.75	3220	22.2	6660	45.9	8350	57.6

\*CONCRETE MIX DESIGN: 600 Lb./Cu. Yd. Of Type I Cement (360 kg/M3) Non air-entrained concrete  
Slump 8.0-9.0 in. (200-230 mm) Dosage rate adjusted to obtain 25-30% water reduction.

**DOSAGE RATES** PolyStrong has a recommended dosage rate of up to 3 fl. oz./cwt (295 mL/100kg) for Type A applications, 3-6 fl. oz./cwt (195-390 mL/100 kg) for use as a mid range, and up to 18 fl. oz./cwt (1,120 mL/kg) for Type F applications. PolyStrong should be added at the end of the mix cycle. The exact dosage depends upon a number of variables and is best determined through field evaluations and the recommendations of a Ridgeview representative.

**NON-CHLORIDE, NON-CORROSIVE** PolyStrong admixture will not initiate or promote corrosion of reinforcing steel embedded in concrete, pre-stressed concrete or concrete placed on galvanized steel floor and roof systems. Calcium chloride is NOT an added ingredient in the manufacture of PolyStrong.

**COMPATIBILITY** Do not mix PolyStrong with naphthalene-based admixtures. For recommendations contact your Ridgeview Concrete Technologies representative.

**PACKAGING** Bulk, totes, 55-gallon drums, 5-gallon pails

**PRECAUTIONS** Care should be taken to maintain product temperature above 40°F. Refer to MSDS for chemical properties.



**Contact Us At:**

**Ridgeview Concrete Technologies**  
16 Lower Hill Road  
Newton, NJ 07860

**Phone: 973.300.5093**  
**Fax: 973.579.1043**

[www.ridgeviewconcretetechnologies.com](http://www.ridgeviewconcretetechnologies.com)

**KEEP CONTAINER TIGHTLY CLOSED.  
KEEP OUT OF REACH OF CHILDREN.  
NOT FOR INTERNAL CONSUMPTION.  
FOR INDUSTRIAL USE ONLY.  
CONSULT MATERIAL SAFETY DATA SHEET FOR MORE INFORMATION.**

Ridgeview Concrete Technologies (RCT) warrants its products to be free of manufacturing defects and that the additives will meet RCT's current published physical properties when applied in accordance with RCT's directions and tested in accordance with ASTM and RCT's standards. There are no other warranties by RCT of any nature whatsoever, expressed or Implied. RCT shall also not be liable for damages of any sort. RCT shall also not be responsible for use of this product in a manner to infringe on any patent held by others.